



Mineral Services: (203) 4810646 – 4810502 - 4810190
Alexandria Port Office: Gate 14, VIP Building 2nd Floor
Head Office : (202) 29179506
E-mail : sgs_egypt@sgs.com
Our Ref. No. : MIN11-1527
Date : 09th August 2011
Issuance : Alexandria,
Certificate No.: F190201/Ore001478

Page: 1 of 1

QUALITY CERTIFICATE

According to Instructions Received from Messer's "LA PACE INTERNATIONAL TRADE CO. LTD.", we attended at Damietta Port for the purpose of quality inspection by indicative sampling & analysis of the under mentioned goods described as follow:

Description of Goods : About 25000 M/T SCREENED SALT IN BULK

PLACE OF INSPECTION : LA PACE open yard store

WE CERTIFY THAT:-

QUALITY:

Sampling:

Samples were carried out by SGS Inspector, identified as indicative samples drawn according to JIS M 8100/1984 method from stock pile La Pace open yard store at Damietta port on **04th August 2011**, all the drawn samples were mixed thoroughly forming gross sample, which divided into four sub-indicative samples, identified, sealed, labeled then distributed as follows:-

- **Two** Sealed and labeled samples, sealed with SGS Seals Nos. I2237727 and I2237728 retained by us for a period of three Months from sampling date unless written instructions received.
- **One** Sealed and labeled sample, sealed with SGS Seal No. I2237729 for analysis propose at SGS Mineral laboratory.
- **One** Sealed and labeled sample, sealed with SGS Seal No. I2237730 handed over to client representative.

Analysis:

Carried out at S.G.S Mineral Lab for sample identified as indicative sample drawn by SGS Inspector and sealed with S.G.S Seals No. I2237729, where the results were as follows:

Chemical Specification:-

Element	Results %	Analysis Method
Moisture	3.07	ASTM E534/2003
Purity (as Sodium Chloride)	98.00	
Insoluble Matter	0.09	
Ca ⁺⁺	0.17	
Mg ⁺⁺	0.31	
SO ₄ ⁻⁻	1.36	
MgSO ₄	1.19	
MgCl ₂	0.27	AAS
CaSO ₄	0.58	
K ⁺	0.03	
Cu ⁺⁺	0.01	
Sieve Analysis:		ASTM E726/2006
+ 8 mm	0.00	
+ 6.7 mm – 8 mm	0.63	
+ 5 mm – 6.7 mm	3.04	
- 5 mm	96.33	

Sampling from any stationary stockpile is considered to be non-truly representative for the obvious reasons: the material is in static condition, not in movement and all the inner layers of material inside the pile are not accessible during sampling from the stockpile.

Sampling will be carried out manually at depth 40cm from the pile's surface. Samplings from stockpiles are always limited.

As a stationary stockpile limited sampling may not be truly representative of the entire cargo lot, the results of analysis may reflect the quality of the collected samples only. Therefore the stockpile pre-loading inspection findings may be used for the indicative / informative or estimation Purposes only prior to loading and none can be used for any kind of commercial final purposes or transactions.

----- End of certificate -----



This document is issued by the Company under its General Conditions of Service printed overleaf. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

SGSPAPER
11054952

